



CIMEC TECHNOLOGIES PRIVATE LIMITED

CIN : U29100GJ2011PTC064482

ISO 9001 : 2015 Certified Company

Regd. Office & Lab 23 / H Meldi Estate, Nr. Gota Railway Crossing, Gota, Ahmedabad - 382481, Gujarat P +91 2717 241209 E info@cimec.in

Technical Queries +91 99250 28369 Customer Care +91 75679 55968



www.cimec.in

TEST REPORT

Format No. : QF/7.8/01

FINAL REPORT

ULR : TC554926000000464F

Customer's Details: Rebar Connect Solution Pvt Ltd

A Top Power, Near Ravki Makhavad Main Road,
Rajkot, Gujarat

Report No. : CT/2601050057
Issue Date : 20/01/2026
Commencement Date : 05/01/2026
Completion Date : 20/01/2026
Page No. : 1/1

Your Ref. No. : Your Letter Date 05/01/2026

Particulars of Sample (as declared by party)

Material Name and Particulars : Coupler (Reinforced Coupler Fe550)
Size : Dia: 25mm, Sampling : Done By Customer,

Date of Receipt : 05/01/2026

Sample Qty : 1Mtr.Approx

Any other information

Name of Client : Deep Radadiya

Name of Consultant/PMC/TPI : Not Declared

Name of Contractor/Agency : Rebar Connect Solution Pvt Ltd

Name of Witness : Not Applicable

Name of Work/Project : Not Declared

Sr. No.	Test Parameter	Unit	Test Method	Specified Requirements As per IS 16172:2023	Observed Value
Group Name : Mechanical Properties of Metal					
Discipline : Mechanical					
1	Static Tensile Strength				
	Tensile Strength	N/mm ²	IS 1608(Pt-1):2022	715 Min. OR If less than 715 N/mm2 the failure should occur in the bar outside the length of mechanical splice	692
	Location of Fracture	-	IS 16172:2023	-	Outside the mech. splice
2	Distance of failure from coupler	mm	IS 16172:2023	-	280
3	Total Slip Value	mm	IS 16172:2023	0.10 Max.	0.051

Remarks : The Grade of TMT Bar is declared by Customer.

End of Report

REVIEWED & AUTHORIZED



SEVAN RATHWA
Lab Incharge
(Authorized Signatory)
CIMEC TECHNOLOGIES PVT. LTD.

NOTE: The above results are related only to the test/s performed on the sample, Endorsement of the product is neither inferred nor implied. This report is not to be reproduced wholly or in part & forbidden to be used as evidence in the court of law & ought not to be used in any advertising media without special permission in writing from Managing Director CIMEC Technologies Pvt. Ltd. Any discrepancies observed in the test report shall be brought to the notice of the Laboratory within one week. Total Liability of CIMEC Technologies Pvt. Ltd. is limited to the invoices amount only. The general condition of service is overleaf.